

15This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



Europäisches Patentamt
European Patent Office
Office européen des brevets



Publication number: **0 688 794 A1**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **95304292.6**

(51) Int. Cl.⁶: **C08F 4/655, C08F 10/02**

(22) Date of filing: **20.06.95**

(30) Priority: **20.06.94 FI 942949**

(43) Date of publication of application:
27.12.95 Bulletin 95/52

(84) Designated Contracting States:
**AT BE CH DE DK ES FR GB GR IE IT LI LU MC
NL PT SE**

(71) Applicant: **BOREALIS POLYMERS OY**
P.O. Box 330
SF-06101 Porvoo (FI)

(72) Inventor: Garoff, Thomas
Borgströmlinkuja 4 K 104
FIN-00840 Helsinki (FI)
Inventor: Johansson, Solveig
Haglingevägen 1
S-44 447 Stenungsund (SE)
Inventor: Palmqvist, Ulf
Hansatie 2
FIN-06150 Porvoo (FI)
Inventor: Lindgren, Daniel
Sörkroken 16
S-44 474 Hjälsby (SE)
Inventor: Stuela, Marita
Käräjätalontie 24
FIN-06100 Porvoo (FI)
Inventor: Waldvogel, Päivi
Päiväläispokku 12
FIN-06450 Porvoo (FI)
Inventor: Kostlainen, Arja
Lehtikujantie 20
FIN-06400 Porvoo (FI)

(74) Representative: **Jennings, Nigel Robin et al**
KILBURN & STRODE
30 John Street
London WC1N 2DD (GB)

(54) **Procatalyst for ethylene polymer production, method for its preparation and use**

(57) The invention relates to a procatalyst for the production of ethylene polymers, which procatalyst comprises an inorganic support, a chlorine compound carried on said support, a magnesium compound carried on said support, a titanium compound carried on said support, whereby the chlorine compound can be different from or the same as the magnesium compound and/or the titanium compound. The activity balance AB of the procatalyst in specified polymerization conditions, is

$$AB > 3.2$$

wherein $AB = [(A + A') : 2] \cdot [\log (MFR_2' : MFR_2) : (A - A')]$, A means polymerization activity expressed as kg PE / g cat · h, MFR_2 means the melt flow rate in g/min units at a load of 2,16 kg, according to the standard ISO

EP 0 688 794 A1

1133, the absence of the upper index ' means low melt flow rate polymerization and the presence of the upper index ' means high melt flow polymerization. This means that the catalyst activity is relatively independent of the presence of chain transfer agents.

The invention relates to a procatalyst component of a Ziegler-Natta catalyst composition which is suitable for production of ethylene polymers. The composition comprises a mixture containing a group III (13) metal, chlorine, magnesium and titanium atoms, supported on a particulate inorganic carrier. The invention also relates to a preparation method and use thereof.

5 Ethylene, alone or with other olefinic unsaturated monomers can often be polymerized in the presence of a catalyst composition, which has essentially two components: a compound of a transition metal belonging to groups 4 to 6 of the Periodic Table of Elements (Hubbard, IUPAC 1970) which is often called a procatalyst, and a compound of a metal belonging to groups 1 to 3 of said Table which is the s.c. cocatalyst. This kind of Ziegler-Natta catalyst composition has been further developed by depositing the
10 procatalyst on a less or more inert and particulate support and by adding to the catalyst composition in the stages of its preparation several additives, among others electron donating compounds. These compounds have improved the polymerization activity of the catalyst, the operating life and other properties of the catalyst composition and first of all properties of the polymers which are obtained by means of the catalyst composition.

15 When ethylene polymers and all other polymers, too, are produced the polymer molecules achieved are not similar by molecular weight, but a mixture having a narrow or broad molecular weight distribution is developed. Different average molecular weights can be defined for the polymer mixtures to describe the most common molecular weight by giving the top value of the distribution, and also several indices have been developed to describe the breadth of the distribution. For controlling the molecular weight we can add
20 to the polymerization reaction a compound called chain transfer agent. In order to obtain polymer products having different molecular weights, a different amount of a compound for controlling the molecular weight must be fed into the polymerization reaction. The most usual and preferable chain transfer agent is hydrogen, because no foreign atoms or atom groups remain in a growing molecule, which can cause inconveniences for the polymerization process or disadvantageous properties of the polymer produced.

25 How well the molecular weight of the produced polymer varies as the function of the hydrogen amount or how much the s.c. hydrogen sensibility changes, greatly depends on the catalyst composition. Generally the problem is, that in polyethylene production the polymerization activity of certain catalyst composition in production of a polymer having high molecular weight is higher, usually many times, even ten times higher, than in the production of a polymer having low molecular weight.

30 This absence of catalyst activity balance is a common drawback for all prior art catalysts today. The imbalance shows up when, using prior art catalysts, a drastic drop in the productivity of the catalysts occurs when going from polymerisation conditions giving high molecular weight polymers (low melt flow) to polymerization conditions giving low molecular weight polymers (high melt flow). Even if this kind of a commercial catalyst can have a quite good productivity at a polymer melt flow rate (MFR, defined according to standard ISO 1133) of 1, there is often only 10 % left of the productivity when producing a MFR of 500.
35 Thus it is desirable to provide a catalyst system having a high activity which is independent from the molar mass of the forming polymer.

A novel procatalyst has now been disclosed by which ethylene homopolymers or copolymers having low or high molecular weight can be produced with an even and high activity. Despite of the amount of
40 hydrogen introduced into the polymerization reactor, a balance of the activities in both cases can be achieved by using a procatalyst composition according to claim 1.

The unique feature of the catalyst according to the disclosure now lies in its good balance in activity in a very wide range of molar mass regulating hydrogen partial pressures used in the polymerization. It is thus possible to carry out an ethylene polymerization by the use of this novel catalyst at high and low melt flow
45 and still have very similar high productivity. This MFR/activity balance renders the catalyst universal applicable for most types of PE resins in all polymerization processes using heterogeneous catalyst systems.

The invention aims simultaneously at maximal catalyst activity and an independence thereof from polymerisation hydrogen pressure, i.e. the melt flow rate of the polymer. Thus, the activity balance AB can
50 be defined so that

$$AB \sim \frac{A' + A}{2} \quad \text{and}$$

$$AB \sim \frac{\log MFR_2' - \log MFR_1}{A' - A}$$

which gives

$$AB = \frac{A' + A}{2} \cdot \frac{\log \frac{MFR_2'}{MFR_2}}{A - A'}$$

wherein

10 AB = activity balance

A = activity in the unit kg PE/g cat.h

MFR₂ = the polymer melt flow rate in g/min using a 2.16 kg load according to the standard ISO-1133

no upper index' = low MFR₂ run

upper index' = high MFR₂ run

15 According to another embodiment of the invention the procatalyst comprises an inorganic support, a chlorine compound carried on said support, a magnesium compound carried on said support and a titanium compound carried on said support. It has been prepared by a process comprising the following steps


a) the inorganic support is contacted with an alkyl metal chloride of the general formula



wherein R is a C₁-C₂₀ alkyl group, Me is a metal of group III(13) of the Periodic Table, n = 1 or 2 and m = 1 or 2, to give a first reaction product,

b) the first reaction product is contacted with a compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium to give a second reaction product,

25 c) the second reaction product is contacted with a titanium compound which contains chlorine, having the general formula




wherein R^{IV} is a C₂-C₂₀ hydrocarbyl group and x is 3 or 4, to give said procatalyst.

The catalyst described in this patent application thus comprises an alkyl metal chloride, which is an internal soluble chlorination agent which also has a cocatalytic impact, a soluble magnesium compound or mixture (named hereafter a magnesium complex) with a sufficiently low viscosity and a titanium compound which contains chlorine. The solubility of the soluble compounds refers to solubility in a non-polar hydrocarbon solution. The catalyst components are deposited on a suitable catalyst support. If a support material is used together with the soluble catalyst components having a sufficiently low viscosity a good morphology can be achieved to the catalyst and thereby to the polymer.

The support material must have a suitable particle size distribution, a high porosity and a large specific surface area. A good result is achieved if the support material has a specific surface area between 100 and 500 m²/g support and a pore volume of 1 - 3 ml/g support. The support material can also be chemically pretreated, e.g. by silanation or by treatment with aluminium alkyls etc. Several metal oxides are suitable, but silicon, aluminium, titanium, chromium and zirconium oxide or mixtures thereof are preferred. Silicon dioxide or silica is most preferable.


45 It is good to dry the support before impregnating by other catalyst components. A good result is achieved if the support is heat-treated at 100 °C to 900 °C for a sufficient time, and thereby the surface hydroxyl groups, in the case of silica, are reduced to below 2 mmol/g SiO₂.

The internal cocatalyst and chlorination agent should be a metal compound containing chlorine that is soluble in non-polar hydrocarbon solvents. A good result is achieved if this compound is an alkylmetalchloride of the type (1):






where R is a C₁-C₂₀ alkyl group, Me is a metal from the group III (13) in the Periodic Table, preferably aluminium, k = 1 or 2 and m is one or two. The alkyl group R can be linear, branched or cyclic, or mixtures thereof, preferably C₂-C₂₀ alkyl. A combination of different chlorination agents can also be used. A good result is achieved if an alkyl aluminium chloride, preferably a lower alkyl aluminium dichloride, most preferably ethyl aluminium dichloride is used.

The magnesium complex used in this catalyst synthesis should be totally soluble in a non-polar hydrocarbon solution. The Mg-complex (compound, mixture) should have the general composition of the formula



wherein X is halogen, preferably chlorine, R' is a hydrocarbon group, preferably a C₂-C₂₀ hydrocarbyl group, that may or may not contain any hetero element, R'' is a C₂-C₂₀ hydrocarbon group and where a > 1, b > 0, c > 0 and d ≥ 0 and molar ratio c/b < 1.

The preferable alternatives of Mg complexes can be represented by formulas (4), (5) or (6) or it can be a mixture thereof:



In (4), (5) and (6) R' and R'' may be different or identical hydrocarbon groups. Preferably they are linear or branched aliphatic or aromatic groups and most preferably R' is an alkyl group and p is 1 < p < 2, and most preferably 1.2 < p < 2.0. OCO is a carboxy group in a carboxylic acid. Essential for the composition is that p must be less than 2.


The compounds (3) to (6) are defined in the following text as the magnesium complexes. A requirement is that in all the compounds (3) to (6) there is a small amount of magnesium alkyl groups. One way to produce these magnesium complexes are to react a soluble magnesium alkyl with an alcohol. To have a good balance of hydrogen response and polymerization activity the MgR₂/ROH feed ratio must be larger than 1:2 and smaller than 1:1, preferably between 1:1.75 and 1:1.99, and most preferably between 1:1.80 and 1.98. This ratio does not have to be created immediately when the magnesium complex is prepared but it can also be created later on, for example after impregnation of the magnesium compound into the support by addition of sufficient amount of MgR₂ to reach the correct MgR₂/ROH feed ratio. The relation between the feed ratio and the complex composition can be obtained from the stoichiometry of the following reaction equation



wherein p is the number of R'''OH moles per one mol of MgR''₂.

The magnesium complex is preferentially the reaction product of a di-C₂-C₂₀-alkyl magnesium, more preferentially dibutyl magnesium, butyl ethyl magnesium or butyl octyl magnesium and an alcohol. The magnesium complex is preferentially the reaction product of a dialkyl magnesium and a branched alcohol, more preferentially a 2-alkyl alkanol, most preferentially 2-ethyl hexanol or 2-propyl pentanol.

The titanium compound can be a chlorinated alcoholate i.e. TiCl₃OR or a solely chloride containing compound such as TiCl₄. The general composition of the compound is (2):



In complex (2) R^{IV} is a C₂-C₂₀ hydrocarbyl group and x is 3 or 4, preferably 4. The Ti compound should be totally soluble in a non-polar hydrocarbon at the temperature applied. If pure TiCl₄ is used there is no need of additional hydrocarbon as this chemical is a liquid.

The alkyl metal chloride having also a cocatalytical effect, can be deposited on the support material as the first chemical in this catalyst synthesis. It is preferable, if the molar ratio between the alkyl metal chloride and the surface hydroxyls of the inorganic oxide is >1, preferably between 1 and 1.5. An even deposition is achieved if the viscosity of the agent or its solution is below 10 mPa·s at the temperature applied. To achieve this low viscosity the alkyl metal chloride agent can be diluted by a non-polar hydrocarbon. The best deposition is however achieved if the total volume of the deposited alkyl metal chloride solution is not exceeding the pore volume of the support, or if the excess of diluting hydrocarbon is evaporated away after the deposition of the alkyl metal chloride. A good choice is to use a 5 - 25 % hydrocarbon solution of ethyl aluminum dichloride. The deposition of the agent can be carried out in a wide range of temperatures, preferably between 0 °C and 110 °C. The chemical addition times and the addition

techniques have to be adjusted to give an even distribution of the chemical in the support material.

A good deposition of the magnesium complex solution is achieved if the volume of the magnesium complex is about two times the pore volume of the support material. This is achieved if the concentration of the complex in a hydrocarbon is between 5 - 60 % in respect of the hydrocarbon used. The ratio between magnesium and chlorine in the alkyl metal chloride agent should be from 1:1.0 to 1:2.5. A good result is achieved if this ratio is from 1:1.5 to 1:2.0.

When depositing the magnesium complex on the support material it should have a viscosity that is lower than 10 mPa·s at the temperature applied. The viscosity of the magnesium complex solution can be adjusted for example by the choice of the group R' in the formulas (3) to (6), by the choice of the concentration of the hydrocarbon solution, by the choice of the ratio between the magnesium alkyl and the alcohol or by using some viscosity lowering agent.

The titanium compound can be added to the support material with or without a previous drying of the catalyst to remove the volatile hydrocarbons. The mol amount of TiCl_4 or corresponding titanium compound should be added to the reaction mixture in a Ti/Mg ratio that is greater than 0.1 and less than one, preferably 1:5-1:1.43. A good result is achieved if the mol ratio Ti/Mg is 0.2 to 0.7. The components should be allowed to react with each other for a sufficient amount of time at a desired temperature. Remaining hydrocarbons can if desired be removed by using slight underpressure, elevated temperature or nitrogen flash.

The procatalyst is prepared as follows:

If a support is used it first is dried as previously mentioned. Then the support is treated with an alkyl metal chloride (1), preferably ethyl-Al-dichloride (EADC), which is bonded on the surface of the carrier particle by reaction with surface hydroxyl groups. Thus a carrier particle is formed on which a s.c. internal cocatalyst with chlorinating influence has been chemically bonded by forming $-\text{O}-\text{Al}-\text{X}_2$ groups. To some extent free alkyl-Al-chloride remains between the support particles.

Next Mg atoms are deposited on support particles. The most common way is to precipitate magnesium from its solution onto the particles. The most easily available Mg compounds, such as the Mg halides, particularly MgCl_2 , do not dissolve in liquid non-polar hydrocarbons, but only in polar solvents. For instance lower aliphatic alcohols, such as methanol or ethanol can be used for the preparation of magnesium alcoholates. The thus formed Mg alcoholates do not completely mix with hydrocarbon solvents, but the mixture thereof will fractionate separate layers. Directly onto the carrier, for instance onto silica, precipitated Mg alcoholate has no polymerization activity. On the other hand, a branched alcohol, for example 2-ethyl hexanol or 2-propyl pentanol, which has a steric hindrance in the molecule close to the Mg-O bond in the Mg-alcoholate and does not coordinate easy and thereby form insoluble compounds. A solution of Mg alcoholate is formed which is completely miscible with liquid hydrocarbons. This kind of hydrocarbon solution is to be developed for the impregnation of carrier particles, so that Mg atoms will be located as even as possible on the carrier particles and also can penetrate into the particle as much as possible when the hydrocarbon is evaporated.

Mg alcoholate is thus prepared from a branched aliphatic monoalcohol and a Mg dialkyl. The alcohol has a sterically bulky hydrocarbon group which prevents it from coordination tightly. In the Mg dialkyl the alkyl group has from 2 to 10 carbon atoms and can be linear or branched. Suitable examples are dibutyl-Mg (DBM), butyl ethyl-Mg (BEM), butyl octyl-Mg (BOMAG) etc. When the Mg alcoholate is prepared, the solution of monoalcohol and Mg dialkyl has a very high viscosity near the stoichiometric equivalent point, thus there are difficulties to carry out the reaction. The viscosity of the solution can be decreased by adding Ti tetraalkoxide, preferably Ti tetrabutoxide to the solution.

When carrier particles are impregnated by the Mg-alcoholate solution which contains a little Mg dialkyl (from 1 to 20 mol-%, preferably about 10 mol-%), the groups $-\text{O}-\text{Al}-\text{X}_2$ on the surface of the carrier particles are converted to groups $-\text{O}-\text{Al}(\text{OR})\text{R}$ and on the surface of the particles MgX_2 molecules are precipitated which both appear from the reaction between Mg compounds and the internal cocatalyst. The alkyl groups R bonded to Al atoms in the surface groups are appeared from Mg dialkyls which very easily react with the internal cocatalyst.

Finally to achieve an active procatalyst, the carrier which is treated as described above is titanized by a four valent Ti halide. A preferable Ti halide is TiCl_4 . In the titanized procatalyst a small amount of the alkoxy and alkyl groups in the Al groups bonded to the carrier are converted to halogen groups and a small amount of TiCl_4 is reduced to the three valent form.

EXAMPLES

The following non-limiting examples are given to illustrate the invention and to compare it to the prior art. First it is described how Mg compound complex is prepared, then the procatalyst synthesis from this complex and other reagents is described, and finally ethylene is polymerized by means of the inventional procatalyst and in comparable examples by means of prior art procatalysts.

Preparation of complex 1

9.5 ml toluene (0.089 mol) and 68.6 ml (0.060 mol) 20% BOMAG-A was added to a septabottle. 16.65 ml (0.1065 mol) 2-ethyl-1-hexanol was added slowly to the reactor. The temperature was kept below 40 °C. The molar ratio between BOMAG-A and 2-ethyl-1-hexanol was 1:1.775.

Preparation of complex 2

6 kg toluene (65.12 mol) and 27.8 kg (33.21 mol) 19,9% BOMAG-A was added to a multipurpose reactor. The reactor was cooled down to 0 °C 7.89 kg (60.45 mmol/g Si) 2-ethyl-1-hexanol was added to the reactor at a speed of 10-30g/min. The temperature was kept below 20 °C. The molar ratio between BOMAG-A and 2-ethyl-1-hexanol was 1:1.8 25.6 kg of this complex was transferred to a container and an aliquot was used for the catalyst prepared in example 1.

Preparation of complex 3

To the complex left in the multi-purpose reactor in complex preparation example 2, another 0.887 kg (6.795 mol) 2-ethyl-1-hexanol was added to complex. Finally 0.34 kg (1 mmol) tetra-isobutoxy-titanium was added. The molar ratio between BOMAG-A and 2-ethyl-hexanol was 1:2.03. The molar ratio between Mg:Ti was 30:1.

Preparation of complex 4

1.53 ml 2-ethyl-1-hexanol was added to 76.8 g of complex 3. The molar ratio between BOMAG-A and 2-ethyl-hexanol became 1:2.19.

Preparation of complex 5

87 kg toluene was added to a reactor. Then 45.5 kg 20.3% BOMAG-A in heptane was also added in the reactor. 161 kg 99.8% 2-ethyl-1-hexanol was feeded in the reactor at the speed of 24 - 40 kg/h. The molar ratio between BOMAG-A and 2-ethyl-1-hexanol was 1:1.83.

Procatalyst preparation

Example 2

54.9 ml (2 mmol/g Si) of 20% EADC was added slowly to 30 g of silica (Crosfield ES70X, activated at 600 °C) at 25 °C. The mixture was stirred for 2.0 h at 20 °C. 81.0 g (2 mmol Mg/g Si) of a complex prepared according to complex preparation 2 was added and stirred for 3.5 h at 20-45 °C. The catalyst was dried at 45-75 °C for two hours. The catalyst was cooled down to 46 °C and 3.33 ml (1 mmol/g Si) TiCl₄ diluted in 10 ml toluene was added to the precursor. The catalyst was stirred over night at 45 °C. The catalyst was dried at 45-70 °C for 2.5 h.

The composition of the dry catalyst was 2.6% Ti, 3.0% Mg, 14.3% Cl and 2.4% Al. The polymerization results are shown in table 1.

Example 3

275 kg silica (Grace 955) activated at 600 °C was charged into a reactor. 411 kg 20% EADC (2.0 mmol/g Si) diluted in 555 l pentane was added to the reactor at ambient temperature during 1 h. The temperature was increased to 35 °C. The treated silica was stirred for 1 h. The treated silica was dried at 50 °C for 8.5 h. 655 kg of the complex (2 mmol Mg/g Si) prepared in complex preparation example 5 was

added at 23 °C during 10 min. 86 kg pentane was added into the reactor at 22 °C during 10 min. The slurry was stirred for 8 h at 50 °C. Finally 52 kg TiCl₄ was added during 0.5 h at 45 °C. The slurry was stirred at 40 °C for 5 h. The catalyst was dried under nitrogen purge.

The composition of the dry catalyst was 2.4% Ti, 2.3% Mg, 14.1% Cl and 2.9% Al.

5 The polymerization results are shown in table 1.

Example 1

10 54.9 ml (2 mmol/g Si) of 20% EADC was added slowly to 30 g of silica (Crosfield ES70X, activated at 600 °C) at 25 °C. The mixture was stirred for 2.5 h at 20 °C. 72.1 g (2 mmol Mg/g Si) of a complex prepared according to complex preparation 1 was added and stirred for 3.5 h at 20-45 °C. The catalyst was dried at 45-75 °C for two hours. The catalyst was cooled down to 46 °C and 3.33 ml (1 mmol/g Si) TiCl₄ diluted in 10 ml toluene was added to the precursor. The catalyst was stirred over night at 45 °C. The catalyst was dried at 45-70 °C for 2.5 h.

15 The composition of the catalyst was 3.2% Ti, 2.4% Mg, 16.4% Cl and 2.8% Al.

The polymerization results are shown in table 1.

Example 4

20 54.9 ml (2 mmol/g Si) of 20% EADC was added slowly to 30 g of silica (ES70X, activated at 600 °C) at 25 °C. The mixture was stirred for 2.0 h at 20 °C. 76.6 g (2 mmol/g Si) of a complex prepared according to complex preparation 3 was added and stirred for 3 h at 20-45 °C. The catalyst was dried at 45-70 °C for two hours. The catalyst was cooled down to 46 °C and 3.33 ml (1 mmol/g Si) TiCl₄ diluted in 10 ml toluene was added to the precursor. The catalyst was stirred over night at 45 °C. The catalyst was dried at 45-70 °C for 2.0 h.

25 The composition of the catalyst was 2.8% Ti, 2.0% Mg, 14.6% Cl and 2.5% Al.

The polymerization results are shown in table 1.

Example 5

30 54.9 ml (2 mmol/g Si) of 20% EADC was added slowly at 25 °C to 30 g of silica (Crosfield ES70X, activated at 600 °C). The mixture was stirred for 2.0 h at 20 °C. 76.7 g (2 mmol Mg/g Si) of a complex prepared according to complex preparation 4 was added and stirred for 3 h at 20-45 °C. The catalyst was dried at 45-70 °C for two hours. The catalyst was cooled down to 46 °C and 3.33 ml (1 mmol/g Si) TiCl₄ diluted in 10 ml toluene was added to the precursor. The catalyst was stirred over night at 45 °C. The catalyst was dried at 45-70 °C for 2.0 h.

35 The composition of the catalyst was 3.0% Ti, 2.1% Mg, 14.4% Cl and 2.7% Al.

The polymerization results are shown in table 1.

40 Polymerization

Ethylene was polymerized in slurry conditions giving products having different average molecular weights or melt flow ratios as follows. 1.8 litres of purified n-pentane was fed into a 3 litre reactor. The mixture was heated up to a temperature 90 °C. In the meantime a 500 ml vessel was pressurized with hydrogen to 500 kPa when polymerizing at low melt flow rate conditions (LMFR) and to 1750 K when polymerizing at high melt flow rate conditions (HMFR). When the temperature 90 °C was reached the pressure was about 420 kPa in the reactor. Then the procatalyst and the cocatalyst triethylaluminium (TEA) were fed into the reactor. The ethylene stream was then conducted through the bomb containing hydrogen into the reactor. The total pressure was increased to 1440 kPa and was maintained by means of continuous ethylene supply. The polymerization went on for one hour. The molar ratio Al/Ti was 15.

The results of the polymerizations are represented in Table 1. In Figure 1 results are represented by diagrams where the polymerisation activity is as function of average molecular weight described as melt flow ratio (defined according to ISO 1133).

55 The procatalyst BC-200 was compared to the old catalysts NC-20 (FI 916192), FI 886056, FI 906281 + FI 895526, a commercial catalyst, and US 4 354 009.

1.8 l of purified isobutan was fed into a 3 l reactor. The content was heated to 95 °C. Meanwhile a 500 ml vessel was pressurized with hydrogen, to 6.2 bar when the polymerization was carried out at low melt flow rate conditions (LMFR), and to 18.7 bar when the polymerization was carried out at high melt flow rate

conditions. When the temperature 95°C was reached, the procatalyst in question and a triethyl aluminum (TEA) cocatalyst were fed to the reactor. Then, ethylene was fed to the reactor through said hydrogen vessel, whereby the total pressure was raised to 28.5 bar and kept constant by feeding ethylene. The molar ratio Al/Ti was 30. The results are disclosed in table 2 and the figure. The AB index of the claimed catalyst BC-200 was clearly higher than that of the old catalysts.

Table 1

Polymerization results presented in examples 1-4

Example	BOMAG: 2-EH molar ratio	MFR ₂ g/min MFR ₂	MFR' ₂	Activity (A) kg PE/g cat.h A	A'	k = log(MFR' ₂ : MFR ₂) = (A-A')	$\bar{A} =$ (A+A'): 2	AB = k· \bar{A}	FRR 21/2	BD kg/m ³	Fines > 0.1 mm	APS mm
1	1:1.775	1.3		5.4					30	340	0.5	1.25
1'	1:1.775		114		2.5	0.6700	3.95	2.647		260	0.6	0.93
2	1:1.820	1.9		3.8					29	360	0.4	1.04
2'	1:1.820		132		3.3	3.6836	3.55	13.08		280	1.0	1.07
3	1:1.830	1.9		4.1					31	390	0.3	0.82
3'	1:1.830		135		4.1	∞	4.10	∞		290	0.3	0.85
4	1:2.02	1.7		4.6					28	350	0.6	1.14
4'	1:2.02		140		1.9	0.6606	3.35	2.213		280	0.8	0.85
5	1:2.19	1.6		4.9					28	340	0.7	1.14
5'	1:2.19		130		1.7	0.5968	3.30	1.969		290	2.6	0.74

BOMAG = Butyloctyl magnesium

2EH = 2-ethylhexanol

EADC = Ethyl aluminum dichloride

LMFR = Low melt flow polymerization conditions

HMFR = High melt flow polymerization conditions

MFR₂ = Melt flow rate for polymer using 2,16 kg weight to ISO 1133

FRR = Flow rate ratio defined as the melt flow ratio MFR₂₁/MFR₂ ISO 1133

BD = Bulk density

APS = Average particle size

The molar ratio Al:Mg:Ti for all examples was 2:2:1

AB = activity balance = $\frac{(A + A')}{2} \cdot \frac{\log(MFR'_2 - MFR_2)}{A - A'}$

Table 2

Sample	Activity (A) kg PE/g cat.h A	Activity (A') kg PE/g cat.h A'	MFR ₂ g/min MFR ₂	MFR' ₂	k = log(MFR' ₂ :MFR ₂) = (A-A')	$\bar{A} =$ (A+A'): 2	AB = k· \bar{A}
Invention FI-906 281	6.0	4.2	2.0	140	1.03	5.1	5.25
+ FI-895 526	9.0	1.1	2.0	200	0.25	5.1	1.28
FI-886 056	6.6	3.4	0.3	32	0.63	5.0	3.15
Commercial	3.7	1.0	0.4	40	0.741	2.4	1.78
Neste NC20	2.3	1.2	1.2	110	1.784	1.75	3.12
US-4 354 009	1.7	0.2	9.0	25	0.296	1.0	0.30

Claims

1. Procatalyst for the production of ethylene polymers, which procatalyst comprises an inorganic support, a chlorine compound carried on said support, a magnesium compound carried on said support, a titanium compound carried on said support, whereby the chlorine compound can be different from or the same as the magnesium compound and/or the titanium compound, characterized in that its activity balance AB in specified polymerization conditions, is

$$AB > 3.2$$

wherein $AB = [(A + A') : 2 \cdot \log (MFR_2' : MFR_2) : (A - A')]$, A means polymerization activity expressed as kg PE / g cat · h, MFR_2 means the melt flow rate in g/min units at a load of 2.16 kg, according to the standard ISO 1133, the absence of the upper index ' means low melt flow rate polymerization and the presence of the upper index ' means high melt flow polymerization.

2. Procatalyst according to claim 1, characterized in that


$$AB > 5$$

3. Procatalyst according to claim 1 or 2, characterized in that said specified polymerization conditions are as follows:

1.8 l of purified n-pentane is fed into a 3 l reactor and heated to a temperature of 90 °C. A separate 500 ml vessel is pressurized with hydrogen to 500 kPa, when the polymerization takes place at low melt flow rate conditions, and to 1750 kPa, when the polymerization takes place at high melt flow rate conditions. When the temperature of the reactor has reached 90 °C, its pressure is approximately 420 kPa. Then, the procatalyst and a triethylaluminium cocatalyst are fed to the reactor at a molar ratio Al:Ti of 15:1. Then a stream of ethylene is conducted through said vessel into the reactor. The total pressure is raised to 1440 kPa and kept constant by feeding ethylene. Polymerization is continued for 1 h after which the ethylene polymer is recovered and analyzed for yield, MFR_2 value, and, based on its yield and amount of used procatalyst, its activity.

4. Procatalyst for the production of ethylene polymers, comprising an inorganic support, a chlorine compound carried on said support, a magnesium compound carried on said support and a titanium compound carried on said support, characterized in that it has been prepared by a process comprising the following steps


a) the inorganic support is contacted with an alkyl metal chloride of the general formula



wherein R is a C_1 - C_{20} alkyl group, Me is a metal of group III(13) of the Periodic Table, $n = 1$ or 2 and $m = 1$ or 2 , to give a first reaction product,

b) the first reaction product is contacted with a compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium to give a second reaction product,

c) the second reaction product is contacted with a titanium compound which contains chlorine, having the general formula



wherein R^{IV} is a C_2 - C_{20} hydrocarbyl group and x is 3 or 4, to give said procatalyst.

5. Procatalyst according to claim 4, characterized in that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) has the following formula or composition






wherein R' is a C_2 - C_{20} hydrocarbyl group containing or not containing a hetero element, R'' is a C_2 - C_{20} -hydrocarbyl group, X is halogen, preferably chlorine, $a \geq 1$, $b > 0$, $c > 0$, $d \geq 0$, $a = 1/2(b+c+d)$

and $c/b < 1$.

6. Procatalyst according to claim 5, **characterized** in that the molar ratio c/b is between approximately 0.05 and 0.1, and that d is 0.

7. Procatalyst according to claim 5 or 6, **characterized** in that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) has one of the following formulas or compositions



wherein $\text{R}'^{\prime\prime}$ is a C_2 - C_{20} hydrocarbyl group, preferably a linear or branched aliphatic or aromatic C_2 - C_{20} group, R'' is said C_2 - C_{20} alkyl group and $1 < p < 2$, preferably $1.78 < p < 1.99$, most preferably $1.80 < p < 1.98$.

8. Procatalyst according to claim 5, 6 or 7, **characterized** in that group R' or $\text{R}'^{\prime\prime}$ is a branched aliphatic C_2 - C_{20} group, preferably an aliphatic C_4 - C_{20} group which is branched in its 2-position with respect to the oxygen, most preferably a 2-lower alkyl- C_3 - C_{19} -alkyl group such as a 2-ethyl hexyl group or a 2-propyl pentyl group.

9. A procatalyst according to any of claims 4-8, **characterized** in that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) is a contact product between a dialkyl magnesium and an alcohol.

10. Procatalyst according to any of claims 4-9, **characterized** in that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) is a contact product of a di- C_2 - C_{10} -alkyl magnesium, preferably dibutyl magnesium, butyl ethyl magnesium or butyl octyl magnesium, and an alcohol.

11. Procatalyst according to any of claims 4-10, **characterized** in that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) is a contact product between a dialkyl magnesium and a branched alcohol, preferably a 2-alkyl alkanol, most preferably 2-ethyl hexanol or 2-propyl pentanol.

12. Procatalyst according to any of claims 4-11, **characterized** in that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) is a contact product between a dialkyl magnesium and an alcohol, the dialkyl magnesium and the alcohol having been contacted at a molar ratio between 1:1.78 and 1:1.99, preferably between 1:1.80 and 1:1.98.

13. Procatalyst according to any of claims 4-12, **characterized** in that in step b) the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium is contacted with the first reaction product so that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium is in a hydrocarbon solution, preferably a hydrocarbon solution, the viscosity of which is below 10 mPas.

14. Procatalyst according to any of claims 4-13, **characterized** in that it has been prepared by a process in said step a) of which the inorganic support is an inorganic oxide, preferably silica, which contains surface hydroxyl groups.




15. Procatalyst according to claim 14, **characterized** in that the inorganic support is an inorganic support, preferably silica, from which a part of its surface hydroxyl groups has been removed, preferably silica containing at the most 2.0 mmol of surface hydroxyl groups per g of silica.

16. Procatalyst according to claim 14 or 15, **characterized** in that in step a), the inorganic oxide which contains surface hydroxyl groups is contacted with an alkyl metal chloride so that the molar ratio

between the alkyl metal chloride and the surface hydroxyls of the inorganic oxide is at least 1, preferably between 1 and 1.5.

17. Procatalyst according to any of claims 4-16, **characterized** in that it has been prepared by a process, in said step a) of which the inorganic support is contacted with an alkyl metal chloride, which is an alkyl aluminum chloride, preferably a lower alkyl aluminum dichloride, most preferably ethyl aluminum dichloride.
18. Procatalyst according to any of claims 4-17, **characterized** in that it has been prepared by a process, in said step a) of which the inorganic support is contacted with an alkyl metal chloride so that the alkyl metal chloride is in the form of a 5-25 % hydrocarbon solution, the viscosity of which preferably is below 10 mPas.
19. Procatalyst according to any of claims 4-18, **characterized** in that the amount of the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) and the alkyl metal chloride of step a) are such that the atomic ratio between the magnesium and the chlorine of the alkyl metal chloride is from 1:1.0 to 1:2.5, preferably between 1:1.5 to 1:2.0.
20. Procatalyst according to any of claims 4-19, **characterized** in that the titanium compound of step c) is titanium tetrachloride.
21. Procatalyst according to any of claims 4-20, **characterized** in that the ratio between the titanium compound of step c) and the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) is such that the atomic ratio between titanium and magnesium is 0.1 Ti/Mg 1, preferably between 0.1 and 0.7.
22. Process for the preparation of a procatalyst for the production of ethylene polymers, said procatalyst comprising an inorganic support, a chlorine compound deposited on said support, a magnesium compound deposited on said support and a titanium compound deposited on said support, **characterized** in that it comprises the following steps
 - a) the inorganic support is contacted with an alkyl metal chloride of the general formula
$$(R_nMeCl_{3-n})_m \quad (1)$$
wherein R is a C₁-C₂₀ alkyl group, Me is a metal of group III(13) of the periodic table, n = 1 or 2 and m = 1 or 2, to give a first reaction product, - b) the first reaction product is contacted with a compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium to give a second reaction product, - c) the second reaction product is contacted with a titanium compound which contains chlorine, having the general formula
$$Cl_xTi(OR^V)_{4-x} \quad (2)$$
wherein R^V is a C₂-C₂₀ hydrocarbyl group and x is 3 or 4, to give said procatalyst.
23. Process according to claim 22, **characterized** in that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) has the following formula or composition
$$Mg_a(OR')_bR''_cX_d \quad (3)$$
wherein R' is a C₂-C₂₀ hydrocarbyl group containing or not containing a hetero element, R'' is a C₂-C₂₀ hydrocarbyl group, X is halogen, preferably chlorine, a ≥ 1, b > 0, c > 0, d ≥ 0, a = 1/2(b + c + d) and c/b < 1.
24. Process according to claim 23, **characterized** in that the molar ratio c/b is between approximately 0.05 and 0.1, and that d is 0.

25. Process according to claim 23 or 24, **characterized** in that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) has one of the following formulas or compositions



wherein R'' is a C₂-C₂₀ hydrocarbyl group, preferably a linear or branched aliphatic or aromatic C₂-C₂₀ group, R'' is said C₂-C₂₀ alkyl group and $1 < p < 2$, preferably $1.78 < p < 1.99$, most preferably $1.80 < p < 1.98$.

26. Process according to claim 23, 24 or 25, **characterized** in that group R' or R'' is a branched aliphatic C₂-C₂₀ group, preferably an aliphatic C₄-C₂₀ group which is branched in its 2-position with respect to the oxygen, most preferably a 2-lower alkyl-C₃-C₁₉-alkyl group such as a 2-ethyl hexyl group or a 2-propyl pentyl group.
27. Process according to any of claims 22-26, **characterized** in that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) is a contact product between a dialkyl magnesium and an alcohol.
28. Process according to claim 27, **characterized** in that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) is a contact product of a di-C₂-C₁₀-alkyl magnesium, preferably dibutyl magnesium, butyl ethyl magnesium or butyl octyl magnesium, and an alcohol.
29. Process according to claim 27 or 28, **characterized** in that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) is a contact product between a dialkyl magnesium and a branched alcohol, preferably a 2-alkyl alkanol, most preferably 2-ethyl hexanol or 2-propyl pentanol.
30. Process according to any of claims 27-29, **characterized** in that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) is a contact product between a dialkyl magnesium and an alcohol, the dialkyl magnesium and the alcohol having been contacted at a molar ratio between 1:1.78 and 1:1.99, preferably between 1:1.80 and 1:1.98.
31. Process according to any of claims 22-30, **characterized** in that in step b) the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium is contacted with the first reaction product so that the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium is in a hydrocarbon solution, preferably a hydrocarbon solution, the viscosity of which is below 10 mPas.
32. Process according to any of claims 22-31, **characterized** in that in said step a) the inorganic support is an inorganic oxide having surface hydroxyls, preferably silica.
33. Process according to claim 32, **characterized** in that the inorganic support is an inorganic support, preferably silica, from which a part of its surface hydroxyl groups has been removed, preferably silica containing at the most 2.0 mmol of surface hydroxyl groups per g of silica.
34. Process according to claim 32 or 33, **characterized** in that in step a), the inorganic oxide which contains surface hydroxyl groups is contacted with an alkyl metal chloride so that the molar ratio between the alkyl metal chloride and the surface hydroxyls of the inorganic oxide is at least 1, preferably between 1 and 1.5.
35. Process according to any of claims 22-34, **characterized** in that in said step a) the inorganic support is contacted with an alkyl metal chloride, which is an alkyl-aluminum-chloride, preferably a lower-alkyl aluminum dichloride, most preferably ethyl aluminum dichloride.

36. Process according to any of claims 22-35, **characterized** in that in said step a) the inorganic support is contacted with an alkyl metal chloride so that the alkyl metal chloride is in the form of a 5-25 % hydrocarbon solution, the viscosity of which preferably is below 10 mPas.

5 37. Process according to any of claims 22-36, **characterized** in that the amount of the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) and the alkyl metal chloride of step a) are such that the atomic ratio between the magnesium and the chlorine of the alkyl metal chloride is from 1:1.0 to 1:2.5, preferably between 1:1.5 to 1:2.0.

10 38. Process according to any of claims 22-37, **characterized** in that the titanium compound of step c) is titanium tetrachloride.

15 39. Process according to any of calims 22-38, **characterized** in that the ratio between the titanium compound of step c) and the compound or mixture containing hydrocarbyl, hydrocarbyl oxide and magnesium of step b) is such that the atomic ratio between titanium and magnesium is $0.1 < \text{Ti/Mg} < 1$, preferably between 0.1 and 0.7.

20

25

30


35

40

45

50

55



FIGURE



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 95 30 4292

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	WO-A-91 16361 (NESTE OY) * page 11, line 34 - page 12, line 25; example 1 * * page 25, line 7 - line 8 * ---	1,2	C08F4/655 C08F10/02
X	EP-A-0 369 436 (UNION CARBIDE CORPORATION) * page 7, line 25 - page 8, line 41; example 1 * * page 7, line 30 - line 31 * * page 10, line 2 - line 9; example 1 * ---	1,2	
P,X	EP-A-0 603 935 (SOLVAY) * example 1 * ---	1,2	
Y	WO-A-94 00498 (NESTE OY) * examples 1,4 * * claims 1-4,7 * ---	4-7,9, 10,14, 17,22	
Y	EP-A-0 173 486 (EXXON RESEARCH AND ENGINEERING COMPANY) * page 14, line 23 - page 15, line 13 * * page 17; example 6; table 1 * ---	4-7,9, 10,14, 17,22	TECHNICAL FIELDS SEARCHED (Int.Cl.6) C08F
A	EP-A-0 032 307 (IMPERIAL CHEMICAL INDUSTRIES LIMITED) * claims 1,3 * * examples 1,3 * -----	4,22	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 26 September 1995	Examiner Fischer, B
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document			